

B19

IONIZING RADIATION-CURABLE INK AND PRINTED MATTER USING THE SAME

Patent number: JP11116875
Publication date: 1999-04-27
Inventor: TAKADA NAOTO; KATO CHIKAKO; URANAKA REIKO
Applicant: TEIKOKU PRINTING INK MFG
Classification:
- international: **B41J2/01; B41M5/00; C09D11/00; G11B7/24; G11B7/254; G11B7/257; B41J2/01; B41M5/00; C09D11/00; G11B7/24; (IPC1-7): C09D11/00; B41J2/01; B41M5/00; G11B7/24**
- european:
Application number: JP19970294946 19971013
Priority number(s): JP19970294946 19971013

Report a data error here

Abstract of JP11116875

PROBLEM TO BE SOLVED: To obtain the subject ink that has sufficient receptivity in no need of long-time heating on its coating by admixing a liquid, water-soluble monomer and a water-absorbing polymer powder thereto. **SOLUTION:** This ink contains (A) 100 pts.wt. of a liquid and water soluble monomer and (B) 60-120 pts.wt., per 100 pts.wt. of the component A, of a powder of water-absorbing polymer. As a component A, is used a monomer that is polymerizable with radiation and compatible with water usually at room temperature at any ratio, for example, a (meth)acrylic ester of a polyhydric alcohol. The component B is a powder of a cross linked polyacrylic acid salt or of polyisobutylene preferably with an average particle size of 2-20 μ m. In the case where ultraviolet rays or visible rays are used as the irradiation, the formulation of a photo-polymerization initiator is recommended thereto in an amount of 2-5 wt.%.

Data supplied from the esp@cenet database - Worldwide